

AKURIT SanaSil

Raum Aktiv

interior silicate colour, highly diffusible (breathable)

- mould-resistant
- coverage 2 and wet-scrub resistance 3
- solvent and plasticiser-free
- low emission
- free from fogging-active substances



Applications

- paint with good coverage on mineral substrates
- optimum final coat for the AKURIT KIP lime interior plaster line
- for a healthy room climate
- for old and new buildings and the restoration sector
- for interior use

Properties

- TÜV externally monitored
- solvent-free
- plasticiser-free
- low emission
- TÜV externally monitored
- organic concentration < 5%
- free from preservatives
- highly water vapour permeable
- good workability

Packaging

- 12.5 l/bucket

Quantity required / Yield

- consumption: approx. 0.20 l/m² per application

Technical Data

Density	1.5 - 1.7 g/cm ³
Wet abrasion resistance	Class 3 according to DIN EN 13300
Coverage	Class 2 according to DIN EN 13300
Gloss	Dull matt according to DIN EN 13300
Yield	6 m ² /l according to DIN EN 13300
Water vapour diffusion resistance μ	36 averaged value
Diffusion-equivalent air layer thickness (s_d -value)	< 0.01 m V1 (high)
Grain size	< 100 μ m S1 (fine)

All of the data provided represents average values that have been determined under laboratory conditions at 23°C and 50% relative air humidity according to the applicable standards and application tests. Deviations under practical conditions are possible.

General notes

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.